

1



WASH/DRY

1. Wash the Car: Use a standard car soap that is free from waxes and silicones. 2. Rinse and Dry: Rinse the car thoroughly, then dry. 3. Optional Clay Bar Treatment: Consider using a clay bar cleaning process for an enhanced finish.

2



APPLY INTENSITY FUELED PRECOAT

Remove swirl marks, micro scratches and prime the surface prior to application of coating by applying *Intensity Fueled Precoat*. Follow the instructions on the bottle of Precoat. If surface is heavily scratched, repeat until smooth. Wipe surface well of all residue, using clean microfiber cloth. **No need to follow with an alcohol cleaning.**

3



APPLICATION

1. Wrap the cloth over the sponge and wet cloth with coating liquid. 2. Proceed to coat by wiping the wet cloth over a 2.0 ft square area, using horizontal and vertical motions with light pressure.



4



WAITING

Wait for the liquid to become almost but not completely dry, anywhere from 1-5 minutes, depending on environmental conditions, especially humidity.

5



WIPE DOWN

Buff with a clean, dry, short nap microfiber cloth. Continue wiping over the area, turning to a fresh section of the towel, until no hazy residue or smearing is present and the coating is completely transparent.

6



CURE TIME

The vehicle can be used after five (5) hours, but the coating will not be fully cured at this time. To ensure optimal performance, avoid allowing water droplets on the surface for the first 3 days, as this may affect the coating. Avoid washing for one (1) week. Anytime after one (1) week, you can apply *Intensity Fueled Spray Coating*.

Micro Detailer, LLC make no warranties, express or implied, including and not limited to, any implied warranty of merchantability or fitness for a particular purpose. Users of this product are totally responsible for determining if this product is suitable for a particular purpose and for user's method of application. If this product is found to be defective, Micro Detailer, LLC's option will be to refund the purchase price or replace the defective product and will not be liable for loss or damage regardless of the legal theory asserted. Copyright Micro Detailer, LLC